



GEOLIFT™2.5 FAST TECHNICAL DATA SHEET

GEOLIFT 2.5 FAST is a hydrophobic two component rigid polyurethane foam system specially formulated for concrete slab lifting purpose by injection process in order to meet the ozone depletion potential (ODP) Global Warming Potential requirements of the Montreal Protocol.

APPLICATIONS		
Sidewalks	$oldsymbol{oldsymbol{oldsymbol{eta}}}$	
Driveways	$oldsymbol{oldsymbol{arphi}}$	
Pool Decks	$oldsymbol{oldsymbol{arphi}}$	
Patios	$oldsymbol{oldsymbol{arphi}}$	
Trip Hazard Remediation	$oldsymbol{oldsymbol{oldsymbol{eta}}}$	
Floor Leveling	$oldsymbol{ol}}}}}}}}}}}}}}}}}}$	
Foundation Repairs	$oldsymbol{ol}}}}}}}}}}}}}}}}}}$	

PHYSICAL PROPERTIES				
		Free Rise	Restrained	
Density	ASTM D 1622	2.0 - 2.3 lb./ft ³	3.8 - 4.0 lb./ft³	
Compressive Strength	ASTM D 1621	25 psi	82 psi	
Compressive Modulus	ASTM D 1621	500 - 800 psi	1100 - 1600 psi	
Shear Strength	ASTM C 273	Under Evaluation		
Tensile Strength	ASTM D 1623	77 psi		
Closed Cell Content	ASTM D 2856	>85%		
Water Absorption	ASTM D 2842	≤1.50% / ≤ 0.08lbs./ft²		
Maximum Service Temperature	300°F			

REACTIVITY PROFILE			
Processing Reactivity Profile	Machine Mix*		
Cream Time (Seconds)	3-5		
Gel Time (Seconds)	8 - 14		
Rise Time (Seconds)	10 - 15		
Tack Free Time (Seconds)	10 - 15		

^{*} Spray Foam Machine (1200psi /Dynamic) liquid components and hoses at 120F°(49°C)

LIQUID COMPONENT PROPERTIES**				
PROPERTY	A-PMDI ISOCYANATE	RESIN		
Color	Brown	Yellow		
Viscosity @ 77°F (25°C)	150 – 250 cps	600 – 750 cps		
Specific Gravity	1.20 – 1.24	1.02 – 1.06		
Shelf Life of unopened drum properly stored	12 months	6 months		
Storage Temperature	50 - 100°F (10 - 38°C)	50 – 100°F (10 – 38°C)		
Mixing Ratio (volume)	100	100		

^{**}See SDS for more information.

PROCESSING PARAMETERS***			
Mixing Ratio A:B A-Side (ISO): B-Side (Resin)	1:1 (Volume)		
Processing Temperature A&B	100 -140°F (38 - 60°C)		
Recirculating Setpoint Temperature A&B	90 -100°F (32 - 38°C)		
Drum Temperature During Processing A&B	70 -90°F (21- 32°C)		
Minimum Processing Pressure A&B	700 psi (4827 kPa)		
Storage Temperature A&B	50 -100°F (10 - 38°C)		
Ambient and Substrate Temperature	>32°F (>0°C)		
Curing Temperature	>32°F (>0°C)		

^{***}Foam application processing temperatures and pressures can vary depending on ambient temperatures, humidity, elevation, substrate, equipment and other factors. It is the sole responsibility of the applicator to process and apply GEOLIFT™ 2.5 FAST within specification.

Disclaimer: GEOLIFT 2.5 FAST is intended to be used solely as a slab jacking polyurethane foam system. The information herein is to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent inferred. All patent rights are reserved. The foam product is combustible and must be protected in accordance with applicable codes. Protect from direct flame and spark contact, around hot work for example. The exclusive remedy for all proven claims is replacement of our materials.